

Reference : T809495 - Fr Etamine I F-22

NF P 92-503 (1995) - "Electric burner "

French decree from 21 November 2002 - Reaction to fire tests on interior materials

End of tests: 1 October 2008

- Sample thickness : ≤ 5 mm
- The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Conditioning

minimum 7 days at (23 ± 2) °C and (50 ± 5) % RH

or
until constant mass is achieved

	length		width	
	face A	face B	face A	face B
Hole formation due to melting	yes	yes	yes	yes
Max. afterflame time (s)	0	0	0	0
Afterglow	no	no	no	no
Afterglow with propagation in area > 25 cm	no	no	no	no
Damaged length (cm)	17	17,5	17	18,5
Damaged width in area >45 cm (cm)	/	/	/	/
Flaming molten droplets	no	no	no	no
Non-flaming molten droplets	yes	yes	yes	yes
Flaming debris	no	no	no	no
Non-flaming debris	no	no	no	no
Average damaged length (cm)	18			