

Reference : T809495 - Fr Etamine I F-22

NF P 92-504 (1995) - "Flame propagation test"
French decree from 21 November 2002 - Reaction to fire tests on interior materials

End of tests: 1 October 2008

- Sample thickness : ≤ 5 mm
- The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Conditioning

minimum 7 days at (23 ± 2) °C and (50 ± 5) % RH
 or
 until constant mass is achieved

Each test has been carried out with a flame application time of 5s.

test	after flame time (s)			
	1	2	3	4
1	*	*	*	*
2	*	*	*	*
3	*	*	*	*
4	*	*	*	*
5	*	*	*	*
6	*	*	*	*
7	*	*	*	*
8	*	*	*	*
9	*	*	*	*
10	*	*	*	*

- * afterflame time ≤ 2 s
- > 2 afterflame time > 2 s and ≤ 5 s
- > 5 afterflame time > 5 s

flaming debris : no

non-flaming debris : yes