

Reference : T809495 - Fr Etamine I F-22

NF P 92-505 (1995) - "Test for melting materials"
French decree from 21 November 2002 - Reaction to fire tests on interior materials

End of tests: 6 October 2008

- Sample thickness : ≤ 5 mm
- The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Conditioning

minimum 7 days at (23 ± 2) °C and (50 ± 5) % RH

or

until constant mass is achieved

Melting behaviour

face A/face B	first ignition (s)	non-flaming debris	flaming debris	ignition cotton wool
1	*	yes	no	no
2	*	yes	no	no
3	*	yes	no	no
4	*	yes	no	no

* no ignition

Conclusion:

M1